

工厂：中国福建省厦门市同安工业集中区思明园117号
 Factory: 117 Siming Yuan, Tong'an Muster Industrial Zone
 Xiamen, Fujian, China
 Tel: (86-592) 5219500 5219600
 Fax: (86-592) 5217833
 Http://www.threestone.com.cn

国际业务部地址：中国福建省厦门市湖里区创业园诚业楼404室
 ADD: Unit 404, Chengye Building, Pioneering Park, Xiamen, 361015, Fujian, China
 Tel: (86-592) 5501369
 Fax: (86-592) 5501269
 E-mail: sales@3Lei.com
 Http://www.3Lei.com



Technical Date Sheet

Product: nylon film 25um

Properties		Test Method	Units	Target Value	Typical Value
Density		N/A	g/cm3	1.15	1.15
Thickness		Q/XMSL 005	Mu	±6%	2.6
Seal Strength		Q/XMSL 005	N/mm	≥7	16
Tensile Strength	MD	Q/XMSL 005	MPa	≥25	36
	TD	Q/XMSL 005		≥25	28
Elongation	MD	Q/XMSL 005	%	≥160	220
	TD	Q/XMSL 005		≥100	201
Heat Shrinkage (200℃, 45min)	MD	Q/XMSL 005	%	≤3.0	1.50%
	TD	Q/XMSL 005		≤3.0	1.30%